## FUSION

### TRAIL SHOE 6A45.20

S3 SRC

**PAG.** 1/2 **SIZES** 36 - 47





CARBONLIGHT TOE CAP



Q-FLEX INSOLE



RESISTANCE TO WATER ABSORPTION



100% NON METALLIC



#### **NORMS** EN ISO 20345:2011

**\$3** - Closed heel area with the following characteristics:

- A Antistatic footwear
- E Heel energy absorption
- FO Resistance to fuel oil of the outsole
- P Penetration resistance sole
- **WRU** Water penetration resistant uppers

#### **ADDITIONAL CHARACTERISTICS:**

**SRC** - Slip resistance on ceramic + sodium lauryl sulfate and steel + glycerin

#### **ADVANTAGES**

Breathable | Comfortable | Excellent anti-slip features | Water-resistant materials

#### **WORKING ENVIRONMENT**

CONSTRUCTION | ENGINEERING | OUTDOOR JOBS





# FUSION

TRAIL SHOE 6A45.20 S3 SRC



PAG. 2/2 CERTIFICATION NUMBER

#### **TECHNICAL INFORMATION**

MATERIALS	STANDARDS	DESCRIPTION	UN.	RESULTS	REQ. EN ISO 20345:2011
<b>UPPER -</b> BLACK NUBUCK LEATHER - Long lasting, flexible and breathable.	6.6+6.8 6.3 6.13	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY TEARING STRENGTH TRANSMITED WATER AFTER 60 MIN ABSORVED WATER 60 MIN	mg/cm² mg/cm² N g %	9,7 83,4 321 0 4.5	min. 0,8 min. 15 min. 120 max. 0,2 max. 30
<b>UPPER LINING -</b> POROMAX - Innovative technology due to th structure of the internal chambers that removes hot and most from the top of the shoe and facilitates the uniform distribution of temperature inside the shoes.	air	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY TEARING STRENGTH	mg/cm <sup>2</sup> mg/cm <sup>2</sup> N	32 256 32	min. 2,0 min. 20 min. 15
<b>HEEL LINING -</b> BLACK TEXTILE - Special mesh fabric for excell breathability. High durability of the materials allows to keep properties throughout the period of use.	5.5.1 6.12	TEARING STRENGTH ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET)	N - -	18 approved approved	min. 15 51.200 25.600
<b>INSOLE -</b> Q-FLEX - Anti-perforation, non-metallic and anti-stat insole.	6.2.1.1	PERFORATION RESISTANCE	N	approved	no perforation
INSOCK - COMFORT - Sotf and light with anti-static points. Easy t remove for cleaning and drying.	5.5.2 7.2	ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET) WATER DESORPTION WATER ABSORPTION	cycles cycles % mg/cm2	approved approved - -	25.600 12.800 min 80 min 70
$\begin{tabular}{ll} \textbf{SOLE -} FUSION BICOLOR PU - Extremely soft and comfortable PU midsole in combination with a hard PU outsole wich provides great the provided of the pr$		TEARING STRENGTH ABRASION RESISTANCE BENDING RESISTANCE OIL RESISTANCE VOLUME VARIATION OIL RESISTANCE INCREASED TOUGHNESS	N/mm mm³ mm % Shore A	10,5 18 0 1,9 <10	min. 8 max. 150 max. 4 max 12 max 10
FULL SHOE	5.11 5.4 5.5 5.14 5.2	SLIP RESISTANCE IN CERAMIC WITH WATER AND DETERGENT SLIP RESISTANCE IN STAINLESS WITH GLYCERINE IMPACT RESISTANCE COMPRESSE STRENGTH SHOCK ABSORPTION (HEEL) ADHESION STRENGTH SOLE/CUT	flat heel flat heel mm mm J N/mm	0,42 0,39 0,18 0,13 13,5 18 80 4,3	min. 0,32 min. 0,28 min. 0,18 min. 0,13 min. 14,0 min. 14,0 min. 20 min. 4,0

SHOE WEIGHT (SIZE 42): 620g

